

ANAIS DA

45^a REUNIÃO ANUAL DA SBO

MACEIÓ, AL

31 de maio a
3 de junho de 2022



Química Para o
Desenvolvimento
Sustentável e
Soberano


Realização



Sociedade
Brasileira
de Química

FERNANDO DE CARVALHO DA SILVA

Anais da 45^a Reunião Anual da SBQ



Maceió - AL
2022

Revisão textual e gramatical: Resposanbilidade dos respectivos autores.

Todos os direitos reservados 2022
A reprodução não autorizada desta publicação, no todo ou em parte,
constitui violação de direitos autorais (Lei 9.610/98).

Dados Internacionais de Catalogação na Publicação (CIP)
(Câmara Brasileira do Livro, SP, Brasil)

Reunião Anual da SBQ (45. : 2022 : Maceió, AL -
online)
Anais da 45ª reunião anual da SBQ [livro
eletrônico] : química para o desenvolvimento
sustentável e soberano / organização Fernando de
Carvalho da Silva. -- Maceió, AL : Aptor Software,
2022.
PDF.

Vários autores.
Bibliografia.
ISBN 978-85-63273-46-8

1. Desenvolvimento sustentável 2. Química
ambiental 3. Química - Estudo e ensino
4. Sustentabilidade I. Silva, Fernando de
Carvalho da. II. Título.

22-118591

CDD-540.7

Índices para catálogo sistemático:

1. Química : Estudo e ensino 540.7

Unexpected luminescent and thermal properties of novel tetrakis Eu^{3+} -indandionate complex: Experimental and theoretical studies

Israel F. Costa (PQ),¹ Lucca Blois (PG),¹ Paulo R. Santos (PG),² Albano N. Carneiro Neto (PQ),³ Renaldo T. Moura Jr. (PQ),⁴ Victor M. Deflon (PQ),⁵ Luís D. Carlos (PQ),³ Wagner M. Faustino (PQ),² Maria Claudia F. C. Felinto (PQ),⁶ Ricardo L. Longo (PQ),⁷ Oscar L. Malta (PQ),⁷ Ercules E.S. Teotonio (PQ),² Hermi F. Brito (PQ).^{1*}

*israelc@iq.usp.br; hefbrito@iq.usp.br

¹Department of Fundamental Chemistry, Institute of Chemistry, University of São Paulo (USP), São Paulo–SP, Brazil; ²Department of Chemistry, Federal University of Paraíba, João Pessoa–PB, Brazil; ³Physics Department and CICECO, University of Aveiro, Aveiro, Portugal; ⁴Department of Chemistry and Physics, Federal University of Paraíba, Areia–PB, Brazil; ⁵São Carlos Institute of Chemistry- University of São Paulo (USP), São Carlos–SP, Brazil; ⁶Nuclear and Energy Research Institute–IPEN/CNEN, São Paulo–SP, Brazil; ⁷Department of Fundamental Chemistry, Federal University of Pernambuco, Recife–PE, Brazil

Keywords: trivalent europium, indandionate, luminescence, Judd-Ofelt parameters, molecular thermometers

Highlights

The highest value of Judd–Ofelt intensity parameter (Ω_2) for the europium compound reported in the literature. The $\text{Et}_4\text{N}^+[\text{Eu}(\text{isovind})_4]^-$ complex presents an abnormal phase transition changing $^5\text{D}_0 \rightarrow ^7\text{F}_J$ luminescence profile.

Resumo/Abstract

Luminescent coordination compounds based on trivalent europium ions (Eu^{3+}) have found wide range of applications in new technologies, such as optoelectronics, molecular thermometers, and biomedical devices. Applications of this materials may be associated with narrow emission bands, which are arise from intra-configurational Laporte forbidden $4f - 4f$ transitions ($^5\text{D}_0 \rightarrow ^7\text{F}_J$). Furthermore, Eu^{3+} ion can act as a powerful spectroscopic probe and the $^5\text{D}_0 \rightarrow ^7\text{F}_2$ transition are strongly sensitive to small angular variations in the coordination polyhedron. However, the energy structures of the organic ligands in the complexes play the most important role on the Eu^{3+} luminescence sensitization process¹. In this context, this work reports about theoretical, syntheses, characterization, and photoluminescence studies of a series of tetrakis complexes containing tetraethylammonium, $\text{Et}_4\text{N}^+[\text{Ln}(\text{L})_4]^-$ (Et_4N^+ : tetraethylammonium cation, Ln: Gd and Eu, and L: 2-acyl-1,3-indandionate). The Judd–Ofelt intensity parameter (Ω_λ), lifetime (τ), radiative (A_{rad}) and non-radiative (A_{nrad}) coefficients, and intrinsic quantum yield ($\Omega_{\text{Eu}}^{\text{Eu}}$) values were calculated for different temperatures (80 - 475 K) (Table 1). The $\text{Et}_4\text{N}^+[\text{Eu}(\text{isovind})_4]^-$ complex, where isovind: 2-isovaleryl-1,3-indandionate) shows an extraordinarily high value of the intensity parameter ($\Omega_2 = 73.5 \times 10^{-20} \text{ cm}^2$, considering the index of refraction equal to 1.5) and radiative decay rate ($A_{\text{rad}} = 2.468 \times 10^3 \text{ s}^{-1}$) at 300 K. These optical results show an abnormally high emission intensity of the $^5\text{D}_0 \rightarrow ^7\text{F}_2$ transition (Figure 1), leading to the highest measured Ω_2 value of the europium materials, to the best our knowledge, reported in the literature. In addition, this complex shows different solid phases at 367 and 460 K, leading significant changes in the band profile assigned to the $^5\text{D}_0 \rightarrow ^7\text{F}_2$ transition. The spectroscopic study of luminescent systems has shown very interesting and promising results for applications, such as OLED devices and luminescent thermometers based on Ln^{3+} ions.

Table 1. Experimental intensity parameters (Ω_λ), lifetime (τ), radiative (A_{rad}) and non-radiative (A_{nrad}) coefficients, and intrinsic quantum yield ($\Omega_{\text{Eu}}^{\text{Eu}}$) of $\text{Et}_4\text{N}^+[\text{Eu}(\text{isovind})_4]^-$ complex.

Temperature K	Ω_2 (10^{-20}) cm^2	Ω_4 (10^{-20}) cm^2	τ (ms)	A_{rad} (s^{-1})	A_{nrad} (s^{-1})	A_{tot} (s^{-1})	$Q_{\text{Ln}}^{\text{Ln}}$ (%)
80	63.6	7.9	0.371	2140	555.4	2695	79.4
200	68.4	8.8	0.358	2307	486.3	2793	82.6
300	73.5	8.9	0.330	2468	562.3	3030	81.4
375	77.7	8.8	0.172	2362	3452	5814	40.6
425	83.1	10.8	0.127	2791	10910	13700	20.4
475	90.5	13.1	0.018	3053	52500	55560	5.5




Figure 1. The emission spectra of $\text{Et}_4\text{N}^+[\text{Eu}(\text{isovind})_4]^-$ complex at from 80 to 475 K. Insert: Photograph taken under the 365 nm UV lamp at 300 K.

Agradecimentos/Acknowledgments

This work was supported by CNPq, FAPESP and CAPES.

¹A.N. Carneiro Neto. *et al.*, Handb. Phys. Chem. Rare Earths, 2019, 55-162.