



3D-Printed Lanthanide-Doped Micropolymers at the Tip of Optical Fibers for Remote Luminescent Temperature Sensing

Ricardo Santos Baltieri¹, Aaron Reupert², Lothar Wondraczek², Danilo Manzani³

¹Instituto de Química de São Carlos - Universidade de São Paulo, ²Friedrich Schiller Universität Jena, ³Instituto de Química de São Carlos - Universidade de São Paulo
(Departamento de Química e Física Molecular)

e-mail: baltieri@usp.br

The integration of 3D printing and lanthanide-based luminescent thermometry enables the development of miniaturized and contactless temperature sensors with high spatial resolution. In this work, we explore two different approaches using Eu^{3+} -doped polymeric microstructures fabricated via two-photon polymerization. The first approach involves direct printing of microstructures at the tip of a multimode silica optical fiber, creating a fiber-integrated sensor for remote temperature monitoring. The second approach employs similar luminescent microstructures printed onto glass slides, expanding the versatility of these materials for planar sensing applications. In the fiber-integrated sensor, temperature sensing is performed using the Luminescence Intensity Ratio (LIR) method, leveraging the complementary emissions of the Eu^{3+} complex and the polymer coating of the fiber. Additionally, RGB colorimetric analysis of optical images enables an alternative approach for temperature evaluation. The sensor demonstrates a stable response in the range of 296 K to 363 K, achieving a maximum relative sensitivity of $5.0\% \text{ K}^{-1}$. The printed structures exhibit remarkable chemical stability in various solvents and maintain their integrity across different thermal conditions, highlighting their potential for robust and high-performance optical sensing. We investigate luminescent microstructures doped with Eu^{3+} , Tb^{3+} , and Sm^{3+} for temperature sensing in the planar substrate approach. Eu^{3+} -doped structures exhibit stable luminescence and efficient energy harvesting from organic ligands, making them highly suitable for thermal sensing. Temperature-dependent luminescence studies reveal complementary behavior between the polymer host and Eu^{3+} emissions. Using LIR and luminescence lifetime analysis, maximum sensitivities of $5.5\% \text{ K}^{-1}$ (360 K) and $5.7\% \text{ K}^{-1}$ (370 K) are achieved, confirming the effectiveness of these microstructures for high-sensitivity temperature detection.

Acknowledgements

FAPESP (2022/15958-4, 2023/05994-6, 2020/11038-2) and Carl Zeiss Foundation Breakthrough Program (2018).

References

R. S. Baltieri et al., *Advanced Materials Technologies*, v. 1, p. 2401877 (2025)